

**PRODUCT:** EVERGLASS® Short Strand Fiber Reinforced Filler

**PART**

<b>NUMBER:</b>	<b>100632</b>	<b>Quart</b>	<b>6 units/case</b>	<b>22 lbs/case</b>
	<b>100622</b>	<b>Gallon</b>	<b>4 units/case</b>	<b>55 lbs/case</b>

**DESCRIPTION:** EVERGLASS® is a multi-fiber reinforced body repair filler ideal for filling holes, rusted metal, body seams, welds and shattered fiberglass.

**FEATURES &**

**ADVANTAGES:** Contains a combination of short strand fibers and Kevlar® for superior strength, durability, and prevention of stress cracks in high stress areas.

Thermal coefficient offers tremendous ability to prevent repair mapping.

Zinc compatible with ZNX-7™ for the ultimate in adhesion and corrosion resistance over steel, galvanized steel and aluminum

Rustproof and waterproof

Can be used over metal and rigid plastics

**USES:**

**COMPOSITES:**

- Shattered Fiberglass
- Rigid Plastic
  - Hoods
  - Deck Lids
  - Fenders
  - Door
  - Pick-up Hatches
  - Ground Effects
  - Spoilers
  - Fender Flares

**METAL:**

- Metal Damage
- Rust Repairs
- Welds
- Panel Bond Seams

**OTHER:**

- Cracks and holes in concrete, masonry, wood and plaster

**SUBSTRATES:**

- |   |  |   |
|---|--|---|
| <ul style="list-style-type: none"><li>▪ Fiberglass</li><li>▪ Rigid Plastics<ul style="list-style-type: none"><li>- SMC</li><li>- RRIM</li><li>- ABS</li><li>- Xenoy</li><li>- Pulse</li><li>- GTX</li><li>- FRP</li></ul></li></ul> | <ul style="list-style-type: none"><li>▪ Bare Steel</li><li>▪ Galvanized Steel</li><li>▪ Aluminum</li></ul> | <ul style="list-style-type: none"><li>▪ Concrete</li><li>▪ Masonry</li><li>▪ Wood</li><li>▪ Plaster</li></ul> |
|---|--|---|

**PREPARATION:** Clean surface thoroughly. Remove all rust, dirt, oil, grease and wax. Use 40-80 grit disc to remove paint. Surface must be completely dry before applying EVERGLASS®.

**MIXING:**

- 1) Place desired amount of filler on a clean, non-fibrous mixing board or hard surface.
- 2) Add a ribbon of cream hardener from edge to edge across a 4" diameter puddle of filler (this equates to 2% by weight). Puddles larger than 4" in diameter will require additional hardener.
- 3) Mix thoroughly until a uniform color is achieved. Approximate setting time is 5-6 minutes @ 75°F to 80°F (27°C).

**APPLICATION:** Spread material on surface forcing it into grind marks, cracks, holes or voids.

**EVERGLASS**

**PAGE 2**

**FINISH:** Sandable in approximately 10-15 minutes. Grind or rough sand hardened filler to desired contour. Apply a finish coat of any EVERCOAT® lightweight body filler or polyester glazing putty.

**TECHNICAL SPECIFICATIONS:**

▪ Appearance	Fibrous Paste
▪ VOC	Packaged: 1.76 lbs/gal (211 g/l)
	Applied: 0.41 lbs/gal (49 g/l)
▪ Weight per Gallon	10.78 lbs/gal.
▪ Viscosity	N/A
▪ Gel Time	3 - 5 min.
▪ Sand Time	10-15 min.
▪ Shore D Hardness	N/A
▪ Lap Shear Adhesion @ 1 hour	745 lbs/ft Galvanized Steel
▪ Corrosion Resistance	Excellent
▪ Water Resistance	No blistering, wrinkling or softening after 24 hours immersion in water.
▪ Max Recommended Thickness (sanded)	1/4 inch
▪ Max Allowable Heat	260°F (126.6°C) Surface Temp
▪ Contents and Caution	MSDS available upon request

**NOTE:** Properties are typical values and should not be considered as sales specifications. Physical Testing performed @ ~77°F (25°C)

**SAFETY & HANDLING:**

Read all directions and warnings prior to using Evercoat® products. Material Safety Data Sheets can be found online at [www.evercoat.com](http://www.evercoat.com).

**NOTES:** Never return mixed filler to can.

Keep can closed and store in a cool dry place

**USE WITH CREAM HARDENER ONLY**

**EVERCOAT®**

Fibre Glass-Evercoat  
a division of Illinois Tool Works Inc.  
6600 Cornell Road • Cincinnati, OH 45242  
(513) 489-7600 Fax (513)489-9229  
[www.evercoat.com](http://www.evercoat.com)  
Made and Printed in the USA

**200-EVG-PIS**

